

Yacht Systems S.r.l. Piazza Tommaseo 4 - 34121 Trieste ITALY Phone +39 040 3783 911 - Fax +39 040 3783 906 E-mail info@venezianiyacht.it - www.venezianiyacht.it

Unigloss one-pack high-quality enamel

Code: 6726....

HIGH-GLOSS FINISH
HIGHEST QUALITY
EXCELLENT LEVELLING

CHARACTERISTICS

One-pack alkyd polyurethane finish. High quality, excellent dilatation and optimum colour and gloss retention. Suitable for use outside and inside pleasure crafts and houses. This product is very flexible and adheres well to a wide range of primers, undercoats and finishes. It cannot be directly applied to inorganic zinc primers or to galvanised panels. Available in various colours. Not suitable for continuous immersion.

* WHITE AND LIGHT COLOURS: s.w. 1,20 +/- 0,02 kg/l

* OTHER COLOUR: s.w. 1,05 +/- 0,05 kg/l

TECHNICAL DATA

Curing mechanism: thinner evaporation and chemical reaction Specific weight: $1.20^* \pm 0.02 \text{ kg/l}$ Solids by volume: 55 % Flash point: +37 °C Appearance: glossy Colour: see colour chart Packaging: 0,75 (only white 2,50) litres

SURFACE PREPARATION

Apply to surfaces which have already been primed or to old paint in good condition which has been sanded, dried and cleaned and which is free from oil, grease and other contaminants. Sand with 300/600 grade abrasive paper to obtain a smooth surface.

APPLICATION

Stir the product well before use until completely homogeneous. The excellent levelling provides a perfect, reflective surface, even when using a brush. To obtain good results, two coats of Unigloss are recommended. This product does not generally require thinning but, if required, add Thinner 5220 up to a maximum of 5% by volume. Apply a uniform, fully wetted coat using cross-strokes to ensure uniform coverage.



Unigloss

APPLICATION DATA

Code: 6726....

Drying time before use (20 °c): ²⁴ h Pot life (20°C):/ °C Application temperature min - max:+5/+35 Hardener: / Mixing ratio by volume: / Mixing ratio by weight: / Thinner: 5220 Wet film thickness per coat: 80 μ Dry film thickness per coat: 40 μ Theoretical coverage per coat: 13.8 m^2/l Overcoating time (20 °C): min 24 max / h. Number of coats: 2

Spray application data	Conventional	Airless
Fluid tip orifice	1,2/1,4 mm.	0,017/0,019 inch.
Air pressure	2,0/3,0 atm.	/
Compression ratio	/	30:1

SAFETY RULES

Adequate ventilation must be provided when applying this product in a confined area and during the subsequent drying period. The product contains solvents which could form an explosive mixture when combined with air and exposed to a naked flame, spark or electrostatic discharge. The wearing of goggles, masks, gloves and protective clothing is recommended.

DISCLAIMER

This edition annuls and replaces all previous issues

Revision date 3-5-05

The information in this data sheet is based on accurate laboratory tests and practical experience, which guarantee the quality of the product if used according to our recommendations. The data contained herein are liable to modification as a result of continuous product development. We do not accept any liability arising from use not in accordance with our recommendations, unless authorized specifically by the Veneziani Technical Services.